



4428

FGADYNE

PLASTER AND GROUT HOSE



CONSTRUCTION: Tube is NR/SBR blend. Cover is a NR/SBR blend, pin-pricked. Reinforcement is four plies of synthetic textile with a static wire.

TEMPERATURE: -40°F (-40°C) to +158°F (+70°C)

BRANDING: Jason logo 4428 PLASTER GROUT WP 800 PSI 55.2 BAR. White mylar longitudinal stripe.





APPLICATION: Used for spraying plaster, grout, sand and gypsym.

FEATURES:

- Cover ozone and weather resistant
- Very good abrasion resistance
- Handles a variety of applications

| Part Number | I.D. | | O.D. | | Reinf. | Max W.P. @ 68°F | | | Weight | | Minimum Bend Radius | | Std. Length |
|----------------|-------|-------|------|-------|--------|--------------------|-------|--------|---------|------|------------------------|-----|----------------|
| | in. | mm | in. | mm | Plies | PSI | BAR | @ 68°F | lb./ft. | KG/m | in. | mm | (ft.) |
| 4428-0150-050 | 1-1/2 | 38.10 | 2.20 | 56.00 | 4 | 800 | 55.20 | n/a | 1.07 | 1.59 | n/a | n/a | 100 |
| 4428-0200-050 | 2 | 50.80 | 2.76 | 70.00 | 4 | 800 | 55.20 | n/a | 1.43 | 2.13 | n/a | n/a | 100 |
| 4428-0250-050 | 2-1/2 | 63.50 | 3.31 | 84.00 | 4 | 800 | 55.20 | n/a | 1.73 | 2.58 | n/a | n/a | 100 |

Working pressure (W.P.) is temperature dependent. See the General Information section Table II - Pressure Re-Rating for increased Temperatures (Page 10) for more information.

All sizes may not be stocked in all locations. Check with customer service for availability.

We disclaim any liability for use of our products in applications other than which they are designed.

SAFETY FACTOR: 3:1